



Synthesis and Structural Characterization of a Novel Indium Mercapto Derivative

$$[\text{ClIn}(\text{SCH}_2(\text{CO})\text{O})_2]^{2-}[(4\text{-MepyH})_2]^{2+}$$

Kulbinder K. Banger
Ohio Aerospace Institute, Brook Park, Ohio

Stan A. Duraj
Cleveland State University, Cleveland, Ohio

Philip E. Fanwick
Purdue University, West Lafayette, Indiana

David G. Hehemann
Cleveland State University, Cleveland, Ohio

Aloysius F. Hepp
Glenn Research Center, Cleveland, Ohio

Robert A. Martock
Cleveland State University, Cleveland, Ohio

The NASA STI Program Office . . . in Profile

Since its founding, NASA has been dedicated to the advancement of aeronautics and space science. The NASA Scientific and Technical Information (STI) Program Office plays a key part in helping NASA maintain this important role.

The NASA STI Program Office is operated by Langley Research Center, the Lead Center for NASA's scientific and technical information. The NASA STI Program Office provides access to the NASA STI Database, the largest collection of aeronautical and space science STI in the world. The Program Office is also NASA's institutional mechanism for disseminating the results of its research and development activities. These results are published by NASA in the NASA STI Report Series, which includes the following report types:

- **TECHNICAL PUBLICATION.** Reports of completed research or a major significant phase of research that present the results of NASA programs and include extensive data or theoretical analysis. Includes compilations of significant scientific and technical data and information deemed to be of continuing reference value. NASA's counterpart of peer-reviewed formal professional papers but has less stringent limitations on manuscript length and extent of graphic presentations.
- **TECHNICAL MEMORANDUM.** Scientific and technical findings that are preliminary or of specialized interest, e.g., quick release reports, working papers, and bibliographies that contain minimal annotation. Does not contain extensive analysis.
- **CONTRACTOR REPORT.** Scientific and technical findings by NASA-sponsored contractors and grantees.

- **CONFERENCE PUBLICATION.** Collected papers from scientific and technical conferences, symposia, seminars, or other meetings sponsored or cosponsored by NASA.
- **SPECIAL PUBLICATION.** Scientific, technical, or historical information from NASA programs, projects, and missions, often concerned with subjects having substantial public interest.
- **TECHNICAL TRANSLATION.** English-language translations of foreign scientific and technical material pertinent to NASA's mission.

Specialized services that complement the STI Program Office's diverse offerings include creating custom thesauri, building customized databases, organizing and publishing research results . . . even providing videos.

For more information about the NASA STI Program Office, see the following:

- Access the NASA STI Program Home Page at <http://www.sti.nasa.gov>
- E-mail your question via the Internet to help@sti.nasa.gov
- Fax your question to the NASA Access Help Desk at 301-621-0134
- Telephone the NASA Access Help Desk at 301-621-0390
- Write to:
NASA Access Help Desk
NASA Center for AeroSpace Information
7121 Standard Drive
Hanover, MD 21076



Synthesis and Structural Characterization of a Novel Indium Mercapto Derivative

$$[\text{ClIn}(\text{SCH}_2(\text{CO})\text{O})_2]^{2-}[(4\text{-MepyH})_2]^{2+}$$

Kulbinder K. Banger
Ohio Aerospace Institute, Brook Park, Ohio

Stan A. Duraj
Cleveland State University, Cleveland, Ohio

Philip E. Fanwick
Purdue University, West Lafayette, Indiana

David G. Hehemann
Cleveland State University, Cleveland, Ohio

Aloysius F. Hepp
Glenn Research Center, Cleveland, Ohio

Robert A. Martock
Cleveland State University, Cleveland, Ohio

National Aeronautics and
Space Administration

Glenn Research Center

Acknowledgments

Aloysius F. Hepp (Director's Discretionary Fund), David G. Hehemann (NASA Cooperative Agreement NCC3-318), Stan A. Duraj (NCC3-162), and Philip E. Fanwick (NCC3-246). We thank Professor Andrew Barron of Rice University and Professor Paul O'Brien of Manchester University, UK, for preprints of their work.

Available from

NASA Center for Aerospace Information
7121 Standard Drive
Hanover, MD 21076

National Technical Information Service
5285 Port Royal Road
Springfield, VA 22100

Available electronically at <http://gltrs.grc.nasa.gov>

**SYNTHESIS, AND STRUCTURAL CHARACTERIZATION
OF A NOVEL INDIUM MERCAPTO DERIVATIVE,
[CIn(SCH₂(CO)O)₂]²⁻[(4-MepyH)₂]²⁺**

Kulbinder K. Banger
Ohio Aerospace Institute
Cleveland, Ohio 44142

Stan A. Duraj
Cleveland State University
Department of Chemistry
Cleveland, Ohio 44115

Philip E. Fanwick
Purdue University
Department of Chemistry
West Lafayette, Indiana 47907

Aloysius F. Hepp^{*}
National Aeronautics and Space Administration
Glenn Research Center
Cleveland, Ohio 44135
Phone: 216-433-3835; Fax: 216-433-6106
E-mail: Aloysius.F.Hepp@nasa.gov

Robert A. Martock
Cleveland State University
Department of Chemistry
Cleveland, Ohio 44115


ABSTRACT

The synthesis and structural characterization of a novel In(III) complex is described. The reaction between InCl₃ with sodium mercapto-acetic acid, (NaSCH₂(CO)OH) in 4-methylpyridine, (CH₃(C₅H₅N), (4-Mepy)) at 25 °C affords [CIn(SCH₂(CO)O)₂]²⁻[(4-MepyH)₂]²⁺, (**1**). X-ray diffraction studies of (**1**) show it to have a distorted square pyramidal geometry, with the [(⁻SCH₂(CO)CO⁻)] ligands in a *trans* conformation. The compound crystallizes in the $\bar{P}1$ (No. 2) space group with $a = 7.8624(6)$ Å, $b = 9.950(1)$ Å, $c = 13.793(2)$ Å, $\alpha = 107.60(1)^\circ$, $\beta = 90.336(8)^\circ$, $\gamma = 98.983(9)^\circ$, $V = 1014.3(4)$ Å³, $R(F_o) = 0.037$ and $R_w = 0.048$.

^{*} Corresponding author

INTRODUCTION

The synthesis of suitable single source Metal Organic Chemical Vapor Deposition, (MOCVD) precursors for the preparation of binary compounds of group 13/16 (IIIB/VIB), has been the recent subject of investigation by a number of groups.¹⁻⁷ Thin films of metal chalcogenides In_xS_y or Ga_xS_y i.e. "midbandgap" semiconductors⁸ (e.g. $\text{InS} = 2.44$ eV and $\beta\text{-In}_2\text{S}_3 = 2.07$ eV) display properties suitable for use in a large array of optoelectronic devices.⁹ The mechanism for decomposition, yields metal sulphide type moieties which can be incorporated into thin-film coatings during fabrication, Scheme I.¹⁰ Therefore, the facile synthesis of these group of compounds, which readily decompose to afford the desired semiconductors with the correct stoichiometry are highly desirable.



Scheme I. Suggested decomposition pathway of metal chalcogenides.

In continuing the development of these types of precursors, we have investigated the preparation of *mono*-thio-oxygen derivatives. An apparent limitation of these complexes is the possibility of oxygen incorporation during thin film growth. However, recent reports in literature successfully demonstrate thin film fabrication using *mono*-thio-oxygen derivatives by MOCVD, which show no oxygen contamination.¹¹⁻¹³

Recently we have synthesized a novel gallium(III) mercapto derivative.⁷ Further to this series, we now report the facile preparation and structural characterization of $[\text{ClIn}(\text{SCH}_2(\text{CO})\text{O})_2]^{2-}[(4\text{-mepyH})_2]^{2+}$, (4-Mepy₂ = $\text{CH}_3(\text{C}_5\text{H}_5\text{N})$), (1).

EXPERIMENTAL

General

Air and moisture-sensitive materials were handled under anaerobic conditions using standard Schlenk line techniques, in flame-dried glassware. Solids were manipulated in a Vacuum Atmospheres dry box equipped with a HE-493 dri-train. Heptane and 4-methylpyridine were distilled from CaH_2 under a dinitrogen atmosphere prior to use. Anhydrous Indium(III)chloride and $[\text{NaSCH}_2(\text{CO})\text{OH}]$ were purchased from Aldrich Chemical Company (Milwaukee, WI) and used without further purification.

Preparation of $[\text{ClIn}(\text{SCH}_2(\text{CO})\text{O})]^{5-}[(4\text{-MepyH})_2]^{2+}$

Sodium mercapto-acetic acid, $(\text{NaSCH}_2(\text{CO})\text{OH})$ (0.64 g, 5.651 mmol) and an InCl_3 , (0.50 g, 2.261 mmol) were reacted in 50 mL of 4-methylpyridine in a Schlenk tube, at ambient temperature under Argon for 7 days. The reaction mixture was then filtered and the collected filtrate layered with 100 mL of heptane. Controlled evaporation, at room temperature subsequently afforded colorless white needles suitable for single crystal analysis.

X-Ray Crystal Data Collection

Single crystal x-ray diffraction data were collected on an Enraf-Nonius CAD4 computer controlled kappa axis diffractometer equipped with a graphite crystal, incident beam monochromator. A colorless needle of $\text{C}_{16}\text{H}_{20}\text{ClInN}_2\text{O}_4\text{S}_2$ having approximate dimensions of 0.50 by 0.17 by 0.13 mm was mounted on a glass fiber. Cell constants and an orientation matrix for data collection were obtained from least-squares refinement, using the setting angles of 25 reflections in the range $20 < \theta < 22^\circ$, measured by the computer-controlled diagonal slit method of centering. The triclinic cell parameters, calculated volume and density are shown in Table I. Crystal quality was determined by measuring several intense omega reflections, which displayed a half height width of 0.57° with a take off angle of 3.0° , indicating moderate crystal quality. There were no systematic absences; the space group was determined to be $\bar{P}1$ (No. 2). A total of 2665 reflections were collected, of which 2665 were unique.¹⁴ Lorentz and polarization corrections were applied to the data. The linear absorption coefficient is 17.0 cm^{-1} for Mo K radiation.

An empirical absorption correction based on the method of Walker and Stuart was applied.¹⁵ Relative transmission coefficients ranged from 0.769 to 1.000 with an average of 0.916.

Table I. Crystallographic data for $C_{16}H_{20}ClInN_2O_4S_2$, (CCDC 170558).

Formula Weight	518.75
Crystal size (mm)	0.50 by 0.17 by 0.13
Space group (No.)	$\bar{P}1$ (No. 2).
A (Å)	7.8624(6)
b (Å)	9.950(1)
c (Å)	13.793(2)
α , (°)	107.60(1)
β , (°)	90.336(9)
γ , (°)	98.983(9)
V, Å ³	1014.3(4)
Z	2
ρ_{calc} , g cm ⁻³	1.698
Temperature, K	293
λ Radiation (wavelength)	Mo K α (0.71073 Å)
μ , cm ⁻¹	15.00
Transmission coeff.	1.000–0.426
Scan method	ω -2 θ
h, k, l,	-8 to 8, 0 to 18, 0 to 15
No. observed data	2665
No. unique data	2665
Largest shift/esd in final cycle	0.15
R(F _o)	0.037
R _w	0.048
F ₀₀₀	520.0
Goodness of fit	1.473

The structure was solved using the solution program Mo1EN on a VAX computer.¹⁶ Interpretation of a Patterson heavy atom method revealed the position of the In atom. The remaining atoms were located in succeeding difference Fourier syntheses. Hydrogen atoms were located and added to the structure factor calculations but not refined. The structure was refined in full-matrix least-squares where w is defined as per the Killean and Lawrence method with terms of 0.020 and 1.0.¹⁷

RESULTS AND DISCUSSION

The indium complex (**1**) was prepared by the stoichiometric reaction of indium(III)chloride and sodium mercapto-acetic acid (NaSCH₂(CO)OH), in 4-methylpyridine, which results in the concomitant deprotonation and ligation of the mercapto derivative. After 7 days, the organic phase is isolated from the grey precipitate and carefully layered with 100 mL of freshly distilled heptane. Slow evaporation at room temperature under inert conditions produced a large quantity of colorless crystals, from which one was selected for analysis by single crystal X-ray diffraction. The product was elucidated as the ionic In(III) species [ClIn(SCH₂(CO)O)]²⁻[(4-MepyH)₂]²⁺ (**1**), (Figure 1, Table II).

Table II. Selected bond distances (Å) and angles (°)
for C₁₆H₂₀ClInN₂O₄S₂.

Bond	Distance/Å	Atoms	Angle/°
In-Cl	2.425(2)	Cl-In-S(1)	108.57(6)
In-S(1)	2.409(2)	Cl-In-S(2)	111.93(6)
In-S(2)	2.407(2)	Cl-In-O(11)	100.1(1)
In-O(11)	2.233(4)	Cl-In-O(21)	95.9(1)
In-O(21)	2.210(4)	S(1)-In-S(2)	139.46(7)
S(1)-C(21)	1.804(6)	S(1)-In-O(11)	82.3(1)
S(2)-C(22)	1.796(7)	S(1)-In-O(21)	95.1(1)
O(11)-C(11)	1.273(7)	S(2)-In-O(11)	88.9(1)
O(21)-C(21)	1.267(7)	S(2)-In-O(21)	82.7(1)
O(12)-C(11)	1.24(2)	O(11)-In-O(21)	163.8(2)
O(12)-H(1)	1.66(7)	In-S(1)-C(12)	97.4(2)
O(22)-H(2)	1.65(6)	In-S(2)-C(22)	97.3(2)
O(22)-C(21)	1.232(7)	In-O(11)-C(11)	119.3(4)
N(101)-H(1)	1.00(7)	In-O(21)-C(21)	119.9(3)
N(202)-H(2)	1.01(6)	O(12)-H(1)-N(101)	172(6)
		O(22)-H(2)-N(201)	172(5)

Compound (**1**) is significant as it represents the first Indium thioglycol complex. The compound exists as a salt of 4-MepyH⁺, which displays a distorted square pyramidal geometry around the indium atom. The ligand-metal interactions are those of a Indium(III) co-ordination sphere with negative charge, (2e⁻) on the bidentate ligand [SCH₂(CO)O⁻] and on the chloride. The In-S and the In-O bond lengths are 2.407(2), 2.409(2) and 2.210(4), 2.233(4) Å respectively, Table II. The thioglycolic derivatives [SCH₂(CO)O⁻], are arranged in the expected *trans* geometry, binding preferentially through the soft donor, since In(III) behaves as a class b, (soft) acceptor. In addition, indium having an underlying d¹⁰ configuration allows it to take part in d_π-p_π back bonding with the thioglycol ligand. In addition, ionic contacts are established between the carbonyl group of the mercapto derivative and the protonated amine, [4-MepyH]⁺, 1.66(7) and 1.65(6) Å.

SUMMARY

In conclusion, the mercapto ligand, [SCH₂(CO)O⁻] belongs to an interesting class of ligand that contains both soft and hard donors sites. Under neutral reaction conditions [SCH₂(CO)OH] has been shown to be a 1e⁻ donor ligand binding through S⁻.¹⁸ However, under basic reaction conditions it is evident that mercapto ligand undergoes deprotonation with reaction with 4-Mepy, thus generating the 2e⁻ ligand [SCH₂(CO)O⁻]. Examination of the C-O bond lengths support these findings. In complex (**1**) bonding is through the soft and hard donor atoms, which account for the observed distorted square pyramidal geometry. Preliminary studies for the use of complex (**1**) for the preparation of indium sulfide films is under investigation.

REFERENCES

1. E.M. Gordon, A.F. Hepp, S.A. Duraj, T.S. Habash, P.E. Fanwick, J.D. Schupp, W. E. Eckles, S. Long, *Inorg. Chim. Acta*, 1997, **257**, 247.
2. A. Graeme, P. O'Brien, A.C. Jones, M. Motevalli, *J. Mater. Chem.*, 2001, **11(9)**, 2346.
3. J. Park, P. O'Brien, A.J. White, D.J. Williams, *Inorg. Chem.*, 2001, **40(14)**, 3629.
4. S.L. Stoll, A.R. Barron, *Chem. Mater.*, 1998, **10(2)**, 650.
5. A.N. Macinnes, W.M. Cleaver, A.R. Barron, M.B. Power, A.F. Hepp, *Adv. Mater. Opt. Electron*, 1992, **1(5)**, 229.

6. S.M. Godfrey, K.J. Kelly, P. Kramkowski, C.A. McAuliffe, R.G. Pritchard, *Chem. Commun.*, 1997, **(11)**, 1001.
7. E.B. Clark, M.L. Breen, P.E. Fanwick, A.F. Hepp, S.A. Duraj, *J. Coord. Chem.*, 2000, **52(2)**, 111.
8. S.M. Sze, "Semiconductor Devices, Physics & Technology," John Wiley and Sons; Chichester, 1985.
9. L.L. Kazmerski, S. Wagner, "Current Topics in Photovoltaics", ed. T. S. Coutts and J. D. Meakin, Academic, London, 1985, 41.
10. A. Bernard, M.M. Borel, G. Lagouche, *Bull. Soc. Chim. Fr.*, 1969, 7066.
11. V.G. Bessergenev, E.N. Ivanona, Y.A. Kovalevskaya, S.A. Gromilov, V.N. Kirichenko, S.V. Lariono, *Inorg. Mater.*, 1996, **32**, 592.
12. G. Zang, K. Kunze, M.J. Hampden-Smith, E.N. Duesler, *Adv. Mater. Chem. Vap. Deposit.*, 1996, **2**, 242.
13. G.A. Horley, M. Chunggaze, P. O'Brien, A.J. White, D.J. Williams, *J. Chem. Soc. Dalton Trans.*, 1998 4205.
14. CCDC reference number 170558, full crystal refinement details for (1), see <http://www.ccdc.cam.ac.uk/>
15. N. Walker, D. Stuart, *Acta Crystallogr.*, 1983, **A39**, 158.
16. Mo1EN, "An Interactive Structure Solution Procedure," Enraf-Nonius, Delft, The Netherlands, 1990.
17. R.G. Killean, J.L. Lawence, *Acta Crystallogr.*, 1969, **B25**, 1750.
18. P. Bishop, P. Marsh, A.K. Brisdon, B.J. Brisdon, M.F. Mahon, *J. Chem. Soc. Dalton Trans.*, 1998, 675.




Figure 1. ORTEP drawing of $[\text{ClIn}(\text{SCH}_2(\text{CO})\text{O})]^{2-}[(4\text{-MepyH})_2]^{2+}$, ($4\text{-Mepy}_2 = \text{CH}_3(\text{C}_5\text{H}_5\text{N})$); thermal ellipsoids enclose 50% of electron density.

REPORT DOCUMENTATION PAGE

Form Approved
OMB No. 0704-0188

Public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden, to Washington Headquarters Services, Directorate for Information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302, and to the Office of Management and Budget, Paperwork Reduction Project (0704-0188), Washington, DC 20503.

1. AGENCY USE ONLY (Leave blank)		2. REPORT DATE July 2004	3. REPORT TYPE AND DATES COVERED Technical Memorandum	
4. TITLE AND SUBTITLE Synthesis and Structural Characterization of a Novel Indium Mercapto Derivative $[\text{ClIn}(\text{SCH}_2(\text{CO})\text{O})_2]^{2-}[(4\text{-MepyH})_2]^{2+}$			5. FUNDING NUMBERS WBS-22-319-20-A1	
6. AUTHOR(S) Kulbinder K. Banger, Stan A. Duraj, Philip E. Fanwick, David G. Hehemann, Aloysius F. Hepp, and Robert A. Martock				
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) National Aeronautics and Space Administration John H. Glenn Research Center at Lewis Field Cleveland, Ohio 44135-3191			8. PERFORMING ORGANIZATION REPORT NUMBER E-13851	
9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES) National Aeronautics and Space Administration Washington, DC 20546-0001			10. SPONSORING/MONITORING AGENCY REPORT NUMBER NASA TM-2004-212289	
11. SUPPLEMENTARY NOTES Kulbinder K. Banger, Ohio Aerospace Institute, Brook Park, Ohio 44142; Stan A. Duraj, David G. Hehemann, and Robert A. Martock, Cleveland State University, Cleveland, Ohio 44115; Philip E. Fanwick, Purdue University, West Lafayette, Indiana 47907; Aloysius F. Hepp, NASA Glenn Research Center. Responsible person, Aloysius F. Hepp, organization code 5410, 216-433-3835, fax: 216-433-6106, e-mail: Aloysius.F.Hepp@nasa.gov.				
12a. DISTRIBUTION/AVAILABILITY STATEMENT Unclassified - Unlimited Subject Category: 25 Available electronically at http://gltrs.grc.nasa.gov This publication is available from the NASA Center for AeroSpace Information, 301-621-0390.			12b. DISTRIBUTION CODE	
13. ABSTRACT (Maximum 200 words) The synthesis and structural characterization of a novel In(III) complex is described. The reaction between InCl_3 with sodium mercapto-acetic acid, $(\text{NaSCH}_2(\text{CO})\text{OH})$ in 4-methylpyridine, $(\text{CH}_3(\text{C}_5\text{H}_5\text{N}), (4\text{-Mepy}))$ at 25°C affords $[\text{ClIn}(\text{SCH}_2(\text{CO})\text{O})_2]^{2-}[(4\text{-MepyH})_2]^{2+}$, (1). X-ray diffraction studies of (1) show it to have a distorted square pyramidal geometry, with the $[(\text{-SCH}_2(\text{CO})\text{CO}^-)]$ ligands in a trans conformation. The compound crystallizes in the $\bar{P}1$ (No. 2) space group with $a = 7.8624(6) \text{ \AA}$, $b = 9.950(1) \text{ \AA}$, $c = 13.793(2) \text{ \AA}$, $\alpha = 107.60(1)^\circ$, $\beta = 90.336(8)^\circ$, $\gamma = 98.983(9)^\circ$, $V = 1014.3(4) \text{ \AA}^3$, $R(F^o) = 0.037$, and $R_w = 0.048$.				
14. SUBJECT TERMS Indium compounds; Crystal structure; Thiols; Pyridines; Photovoltaics; Coordination			15. NUMBER OF PAGES 11	
			16. PRICE CODE	
17. SECURITY CLASSIFICATION OF REPORT Unclassified	18. SECURITY CLASSIFICATION OF THIS PAGE Unclassified	19. SECURITY CLASSIFICATION OF ABSTRACT Unclassified	20. LIMITATION OF ABSTRACT	

